

## **Background**

AquaGate+PAC (Powdered Activated Carbon) is a patented, composite-aggregate technology resembling small stones typically comprised of a dense aggregate core, clay or clay-sized materials, polymers, and fine-grained activated carbon additives.




Figure 1. Configuration of PAC-coated particle.

AquaGate+PAC serves as a delivery mechanism to reliably place reactive capping materials into aquatic environments.



## **Product Specifications**

Aggregate: Nominal AASHTO #8 (1/4-3/8") or custom-sized to meet project-specific need

\* Limestone or non-calcareous substitute, as deemed project-appropriate

Clay: Bentonite (or montmorillonite derivative)

\* Typically 5 – 10% by weight

Activated Carbon: Powdered

99% (minimum) through 100 mesh sieve 95% (minimum) through 200 mesh sieve 90% (minimum) through 325 mesh sieve

\* Typically 5% by weight (+/- 25%)

Binder: Cellulosic polymer

Permeability:  $1 \times 10^{-1}$  to  $1 \times 10^{-2}$  cm/sec

Dry Bulk Density: 70 – 90 lbs/ft<sup>3</sup>

Moisture: 10 - 12% (maximum)



For more information, contact AquaBlok, Ltd. at:

Phone: (419) 825-1325 Email: services@aquablok.com Web: www.aquablok.com

© 2017 AquaBlok, Ltd.

Last Revised: May 2017